

GSU Glazes

Cone 10 Recipes

Purple Haze (C9-10R)

Custer Feldspar	50
Whiting	8.8
Gerstley Borate	6.9
Dolomite	6.4
Zinc Oxide	4.2
EPK	2.7
Silica	21.3

Tin Oxide	3.2
Titanium Oxide	3.5
Copper Carbonate	1.1

Bella Red (C9-10R)

Nepheline Syenite	20.4
Whiting	15.7
Minspar	15.5
Gerstley Borate	10.8
Grolleg Kaolin	1.4
Silica	35.9
--	
Tin Oxide	1.7
Copper Carbonate	0.4

Celadon (C9-10R)

G200	45.4
Whiting	22.7
Kaolin	11.36
--	
Red Iron Oxide	2.28

China Blue (C9-10R)

Custer Feldspar	42.1
Dolomite	8.8
Gerstley Borate	8.8
Barium Carbonate	4.4
Whiting	2.6
Zinc Oxide	1.7
Silica	27.2
--	
Bentonite	2
Tin Oxide	2.6
Red Iron Oxide	2
Cobalt Oxide	0.5

Coleman's Patina Green (C10R)

Custer Feldspar	52
Barium Carbonate	38
EPK	10
--	
Rutile	8
Copper Carbonate	4

Buttermilk (C9-10R)

G200	29.3
Gerstley Borate	10.5
Dolomite	6.8
Talc	13.5
Whiting	9
Silica	24.1
--	
Zircopax	8

Joerling Shino (9-10R)

Nepheline Syenite	41
F-4 Feldspar	10
Ball Clay	18
Soda Ash	17
Redart	6

Mellow Yellow (C9-10R)

Nepheline Syenite	71.6
Dolomite	23.6
Ball Clay	4.8
--	
Bentonite	4
Red Iron Oxide	1.1
Zircopax	17.9

Tenmoku (C9-10R)

G-200	52.66
Whiting	19.58
Zinc Oxide	2.72
Kaolin	11.8
Silica	26.34
--	
Red Iron Oxide	9.08

Cone 6-10 Slips

White Slip (slip base)

EPK	43.76
F4 Feldspar	23.48
Silica	15.58
Bentonite	9.39
Pyrophyllite	7.79

Black Slip

EPK	43.76
F4 Feldspar	23.48
Silica	15.58
Bentonite	9.39
Pyrophyllite	7.79
--	
Black Stain	10